

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C08G 18/66, 18/48	A1	(11) International Publication Number: WO 97/21750 (43) International Publication Date: 19 June 1997 (19.06.97)
<p>(21) International Application Number: PCT/EP96/05035</p> <p>(22) International Filing Date: 14 November 1996 (14.11.96)</p> <p>(30) Priority Data: 95203405.6 8 December 1995 (08.12.95) EP (34) Countries for which the regional or international application was filed: AT et al.</p> <p>(71) Applicant: IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB).</p> <p>(72) Inventors: BLEYS, Gerhard, Jozef; Bremstraat 19, B-3001 Heverlee (BE). HAMILTON, Alan, James; Dorpstraat 597, B-3061 Leefdaal (BE). LEENSLAG, Jan, Willem; Rechtestraat 10, B-3120 Tremelo (BE).</p> <p>(74) Agents: BAKEN, Philippus, Johannes, Leonardus, Henricus et al.; ICI Europe Ltd., ICI Polyurethanes, Intellectual Property Dept., Everslaan 45, B-3078 Everberg (BE).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published With international search report.</p>
<p>(54) Title: POLYURETHANE ELASTOMERS</p> <p>(57) Abstract</p> <p>A polyisocyanate-based elastomer having a ratio of the storage modulus (E') at 20 °C and the storage modulus (E') at 120 °C of between 0.75 and 1.5, a tan δ at 100 °C of less than 0.1 and a maximum value of the tan δ of more than 0.8, the tan δ being the ratio of the loss modulus (E'') and the storage modulus (E').</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

POLYURETHANE ELASTOMERS

DESCRIPTION

5 The present invention relates to novel polyurethane elastomers and a method for the preparation thereof.

10 Polyurethane elastomers are made by reacting diisocyanates, such as toluene diisocyanate (TDI), 1,5 naphthalene diisocyanate (NDI) or 4,4' diphenylmethane diisocyanate (4,4'-MDI), with high molecular weight polyols, such as polyester polyols or polyether polyols, and low molecular weight polyols or polyamines, such as ethylene glycol or butane diol.

15 High molecular weight polyether polyols mainly used are polytetrahydrofuran or polypropyleneoxide.

20 The preparation of elastomeric polyurethanes from polyether polyols containing minor amounts of ethylene oxide (EO)-groups is also known, see for example EP-A-13487.

Formulations comprising high amounts of 4,4'-MDI and polyether polyols having high EO-contents have already been used to prepare flexible polyurethane foams, see for example EP-A-547764, EP-A-547765 and EP-A-549120.

25 None of the known isocyanate-based elastomers however shows satisfactory dynamic modulus behaviour over a broad temperature range.

30 A new class of polyurethane elastomers has now been found which show a quasi-perfect elastomeric behaviour over a broad temperature range.

Thus, the present invention relates to polyisocyanate-based elastomers having a ratio of the storage modulus (E') at 20°C and the storage modulus (E') at 120°C of between 0.75 and 1.5, a $\tan \delta$ at 100°C of less than 0.1 and a maximum value of the $\tan \delta$ of more than 0.8, the $\tan \delta$ being the ratio of the loss modulus (E'') and the storage modulus (E').

35 Preferably, the maximum value of the $\tan \delta$ is more than 1.0.

40 The ratio of the storage modulus (E') at 20°C and the storage modulus (E') at 120°C is preferably between 0.8 and 1.2, and most preferably between 0.85 and

1.1.

It is preferred to have a $\tan \delta$ at 100°C of less than 0.05. Most preferably the $\tan \delta$ at 100°C is less than 0.03.

The prime maximum of the $\tan \delta$ preferably occurs at a temperature below 0°C, most preferably below -10°C.

The storage and loss modulus are measured by Dynamic Mechanical Thermal Analysis (DMTA measured according to ISO/DIS 6721-5).

These novel polyurethane elastomers can be made from formulations containing polyols having high oxyethylene contents or polyol blends containing polyester polyols and high concentrations of polyols having high oxyethylene contents, substantially pure 4,4'-MDI or a derivative thereof, and a low molecular weight chain extender and optionally a crosslinking agent.

Thus, according to the invention, there is also provided a method for the preparation of polyurethane elastomers from a reaction mixture comprising a polyisocyanate component, a polyol composition, a chain extender and optionally a crosslinking agent wherein the polyisocyanate component contains at least 85% by weight of 4,4'-diphenylmethane diisocyanate or a variant thereof, the polyol composition comprises at least one polyoxyalkylene polyol containing oxyethylene residues, said polyol composition having an average nominal hydroxyl functionality of from 2 to 4, an average hydroxyl equivalent weight of from 500 to 7000 and an average oxyethylene content of between 50 and 85% by weight, and the chain extender has an average hydroxyl equivalent weight of up to 250.

The polyisocyanate component used in the invention may be any aromatic or aliphatic polyisocyanate such as TDI, NDI or pure 4,4'-diphenylmethane diisocyanate or mixtures of that diisocyanate with one or more other organic polyisocyanates, especially other diphenylmethane diisocyanate isomers, for example the 2,4'-isomer optionally in conjunction with the 2,2'-isomer. The polyisocyanate component may also be an MDI variant derived from a polyisocyanate composition containing at least 85% by weight of 4,4'-diphenylmethane diisocyanate. MDI variants are well known in the art and, for use in accordance with the invention, particularly include liquid products obtained by introducing uretonimine and/or carbodiimide groups into said polyisocyanate composition and/or by reacting with one or more polyols.

Preferred as the polyisocyanate component are polyisocyanate compositions containing at least 90% by weight of 4,4'-diphenylmethane diisocyanate. Polyisocyanate compositions containing at least 95% by weight of 4,4'-diphenylmethane diisocyanate are most preferred.

5

The polyol composition may consist of one or more polyether polyols optionally blended with other polyols, such as polyester polyols.

10

The composition may comprise a single polyoxyalkylene polyol which preferably is a poly(oxyethylene-oxypropylene) polyol having the required functionality, equivalent weight and oxyethylene content. Such polyols are known in the art and may be obtained in conventional manner by reacting ethylene and propylene oxides simultaneously and/or sequentially in any order with an initiator such as water, a polyol, a hydroxylamine, a polyamine and the like having from 2 to 4 active hydrogen atoms.

15

Alternatively, the polyol composition may comprise a mixture of two or more polyoxyalkylene polyols such that the total composition has the required average functionality, equivalent weight and oxyethylene content. The polyoxyalkylene polyols present in such mixtures are preferably poly(oxyethylene-oxypropylene) polyols but one or more polyoxyethylene polyols and/or polyoxypropylene polyols may also be present.

20

Preferred polyether polyol compositions comprise:

25

- (a) from 75 to 100% by weight of a first polyol component comprising at least one polyoxyalkylene polyol containing oxyethylene residues, said polyol component having an average nominal hydroxyl functionality of from 2 to 4, an average hydroxyl equivalent weight of from 1000 to 5000 and an average oxyethylene content of from 60 to 85% by weight, and
- (b) from 25 to 0% by weight of another polyol component.

30

Polyol component (b) suitably has an average functionality of from 2 to 4, an average equivalent weight of 1000 to 3000 and may be, for example, a polyoxypropylene polyol, a polyoxyethylene polyol or a poly(oxyethylene-oxypropylene) polyol containing less than 60% or more than 85% by weight of oxyethylene residues.

35

The term "average nominal hydroxyl functionality" is used herein to indicate the average functionality (number of hydroxyl groups per molecule) of the polyol composition on the assumption that the average functionality of the

40

polyoxyalkylene polyols present therein is identical with the average functionality (number of active hydrogen atoms per molecule) of the initiator(s) used in their preparation although in practice it will often be somewhat less because of some terminal unsaturation.

It is preferred that the average nominal hydroxyl functionality of the polyol composition is from 2 to 3.

If desired, the polyoxyalkylene polyol (or one or more of the polyoxyalkylene polyols when a mixture is used) may contain dispersed polymer particles. Such polymer modified polyols have been fully described in the prior art and include products obtained by the in situ polymerisation of one or more vinyl monomers, for example acrylonitrile and styrene, in polyoxyalkylene polyols or by the in situ reaction between a polyisocyanate and an amino-or hydroxy-functional compound, for example triethanolamine, in the polyoxyalkylene.

Also suitable as polyol (b) are polyester polyols.

Polyester polyols which may be used include hydroxyl-terminated reaction products of polyhydric alcohols such as ethylene glycol, propylene glycol, diethylene glycol, dipropylene glycol, 1,4-butanediol, bis(hydroxyethyl) terephthalate, glycerol, trimethylolpropane, hexanediol, neopentyl glycol, methylpentane diol, pentaerythritol or polyether polyols or mixtures of such polyhydric alcohols, and polycarboxylic acids, especially dicarboxylic acids or their ester-forming derivatives, for example succinic, glutaric and adipic acids or their dimethyl esters, sebacic acid, phthalic anhydride, tetrachlorophthalic anhydride or dimethyl terephthalate or mixtures thereof.

Preferred polyesters have a number average molecular weight of 750-4000, especially 750-2500, and an average nominal functionality of 2-3.

Suitable chain extenders include low molecular weight diols, aminoalcohols or diamines such as ethylene glycol, diethylene glycol, dipropylene glycol, tripropylene glycol, propanediol, butanediol, pentanediol, hexanediol, 3-methylpentane-1,5-diol, ethanolamine or diethyltoluenediamine.

Low molecular weight isocyanate-reactive compounds having an average functionality of 3 or more, such as glycerol, pentaerythritol or triethanolamine, may be added as crosslinking agents.

It is preferred to add small amounts of water, most preferably less than 2%

by weight based on the total weight of the isocyanate-reactive, to the formulation. The isocyanate-index of the reaction system, taking account of the polyol composition, water and any other isocyanate-reactive species, for example chain extenders and opt. crosslinking agents, may be as low as 85 or
5 as high as 120. Preferably, the isocyanate index is between 90 and 110. The most preferred isocyanate-index is between 95 and 105.

The elastomer-forming reaction mixture may contain one or more of the additives conventional to such reaction mixtures. Such additives include
10 catalysts, for example tertiary amines and tin compounds, surface-active agents and foam stabilisers, for example siloxane-oxyalkylene copolymers, flame retardants, organic and inorganic fillers, pigments, and internal mould release agents.

15 The invention furthermore provides a reaction system comprising:

- (a) a polyisocyanate component containing at least 85% by weight of 4,4'-diphenylmethane diisocyanate or a variant thereof;
- (b) a polyol composition comprising at least one polyoxyalkylene polyol
20 containing oxyethylene residues, said polyol composition having an average nominal hydroxyl functionality of from 2 to 4, an average hydroxyl equivalent weight of from 500 to 7000 and an average oxyethylene content of between 50 and 85% by weight;
- (c) a chain extender having an average hydroxyl equivalent weight of up to
25 250, and optionally,
- (d) water,
- (e) a crosslinking agent, and
- (f) one or more additives conventional to elastomer formulations.

30 This reaction system is used for making polyurethane elastomers.

In operating the method of the invention, the known one-shot, semi-prepolymer or full prepolymer techniques may be applied together with mixing equipment conventionally used in the preparation of elastomers.

35 The elastomers according to the invention are particularly suitable for use in applications where good energy-absorbing and fatigue properties are required and a good elastomeric behaviour over a broad temperature range, e.g. in the automotive and footwear industry.

-6-

The invention is illustrated by the following examples in which all parts, percentages and ratios are by weight.

5 The following glossary of materials is included to identify reaction components not otherwise identified in the examples.

GLOSSARY

- 5 Polyisocyanate I: pure 4,4'-MDI (Suprasec MPR; commercially available from Imperial Chemical Industries PLC; Suprasec is a trademark of ICI PLC).
- 10 Polyisocyanate II: uretonimine-modified MDI (Suprasec 2020; commercially available from Imperial Chemical Industries PLC).
- 10 Polyisocyanate III: MDI-based prepolymer (Suprasec 2433; commercially available from Imperial Chemical Industries PLC)
- 15 Polyisocyanate IV: isocyanate prepolymer made by reacting polyisocyanate I and polyol B (NCO-content = 8.66%).
- 15 Polyol A: EO/PO triol having 70% random EO-groups; OH-value of 42 mg KOH/g and about 45% primary OH-groups.
- 20 Polyol B: EO/PO diol having 75% random EO-groups and OH-value of 27 mg KOH/g.
- 20 Polyol C: 70/30 blend of an EO/PO diol (22% EO-tip; OH-value = 35mg KOH/g) and an EO/PO triol (15% EO-tip; OH-value = 32 mg KOH/g).
- 25 Polyol D: polymer-modified polyol (glycerol-initiated polyol having OH-value = 34 mg KOH/g; 15% EO-tip; 75% primary OH-groups and containing 20% styrene-acrylonitrile copolymer particles).
- 30 Polyol E: EO/PO diol having 27% EO-tip and OH-value of 30 mg KOH/g.
- 35 Catalyst 1: Dabco EG; commercially available from Air Products.
- 35 Catalyst 2: Niax A1; commercially available from Union Carbide.
- EG: ethylene glycol

EXAMPLESExamples 1,2,3 and 4 and comparative examples 1 and 2

Elastomers were bench mixed and moulded in a 15 x 10 x 1 cm mould in a conventional manner using the formulations given in Table I and the properties indicated in Table I were measured.

Table I

	1	2	3	4	Comp.1	Comp.2
Polyisocyanate I	36.4	42.7	-	-	-	-
Polyisocyanate II	-	-	46.8	-	-	42.9
Polyisocyanate III	-	-	-	-	109	-
Polyisocyanate IV	-	-	-	100	-	-
Polyol A	100.0	50.0	-	-	-	-
Polyol B	-	50.0	100.0	-	-	-
Polyol C	-	-	-	-	100.0	-
Polyol D	-	-	-	-	28.3	-
Polyol E	-	-	-	-	-	100.0
Ethylene glycol	5.0	7.0	7.0	4.55	8.9	6.0
Water	0.3	0.3	0.3	0.21	0.6	0.3
Catalyst 1	1.0	0.5	1.0	0.7	2.6	1.0
Catalyst 2	-	-	-	-	0.4	-
Moulded density (kg/m ³)	450	440	440	580	490	585
Hardness	46 (Asker C)	51 (Asker C)	41 (Asker C)	62 (Asker C)	47 (Shore A)	N.M.*
E' (20°C)/E' (120°C) ratio	0.95	1.01	0.98	0.86	1.69	2.19
tan δ (100°C)	0.002	0.013	0.024	0.005	0.070	0.078
tan δ_{max} (temperature in °C)	-23	-26	-11	-11	-43	-45
tan δ_{max} (value)	1.08	0.86	1.01	1.22	0.42	0.37

*N.M. = not measured

The E' (20°C)/E (120°C) ratio of the elastomers according to the comparative examples is higher than 1.5 and their maximum value of the tan δ is less than 0.8.

DMTA-test

Measurements were carried out according to ISO/DIS 6721-5 on a Rheometric Scientific DMTA apparatus using a 3-point bending method. Sample test dimensions were: length 1.0 cm, width 1.3 cm, thickness 0.4 cm. Applied strain amplitude 64×10^{-4} cm, frequency 1 Hz, heating rate 2°C/min. The elastomer samples were pre-conditioned at 23°C/50% RH for 24 hours prior testing. The elastomer samples were quenched to -120°C (cooling rate 8.5°C/min) and held at that temperature for 5 minutes before heating of the sample was started.

Figures 1-4 show the DMTA-curves of the examples 1-4. The DMTA-curves of the comparative examples 1 and 2 are shown in figures 5 and 6.

CLAIMS

1. A polyisocyanate-based elastomer having a ratio of the storage modulus (E') at 20°C and the storage modulus (E') at 120°C of between 0.75 and 1.5, a $\tan \delta$ at 100°C of less than 0.1 and a maximum value of the $\tan \delta$ of more than 0.8, the $\tan \delta$ being the ratio of the loss modulus (E'') and the storage modulus (E').
2. An elastomer according to claim 1 wherein the polyisocyanate contains at least 90% by weight of 4,4'-diphenylmethane diisocyanate.
3. An elastomer according to claim 2 wherein the polyisocyanate contains at least 95% by weight of 4,4'-diphenylmethane diisocyanate.
4. An elastomer according to any one of the preceding claims having a ratio of the storage modulus (E') at 20°C and the storage modulus (E') at 120°C of between 0.8 and 1.2.
5. An elastomer according to claim 4 having a ratio of the storage modulus (E') at 20°C and the storage modulus (E') at 120°C of between 0.85 and 1.1.
6. An elastomer according to any one of the preceding claims having a $\tan \delta$ at 100°C of less than 0.05.
7. An elastomer according to claim 6 having a $\tan \delta$ at 100°C of less than 0.03.
8. An elastomer according to any one of the preceding claims having a maximum value of the $\tan \delta$ of more than 1.0.
9. An elastomer according to any one of the preceding claims having the prime maximum of the $\tan \delta$ at a temperature below 0°C.
10. An elastomer according to claim 9 having the prime maximum of the $\tan \delta$ at a temperature below -10°C.
11. A method for the preparation of elastomers according to any one of the preceding claims from a reaction mixture comprising a polyisocyanate component, a polyol composition, a chain extender and optionally a

crosslinking agent wherein the polyisocyanate component contains at least 85% by weight of 4,4'-diphenylmethane diisocyanate or a variant thereof, the polyol composition comprises at least one polyoxyalkylene polyol containing oxyethylene residues, said polyol composition having an average nominal hydroxyl functionality of from 2 to 4, an average hydroxyl equivalent weight of from 500 to 7000 and an average oxyethylene content of between 50 and 85% by weight, and the chain extender has an average hydroxyl equivalent weight of up to 250.

12. A method according to claim 11 wherein the polyol composition comprises at least one poly(oxyethylene-oxypropylene) polyol.

13. A method according to claim 12 wherein the polyol composition comprises:

- (a) from 75 to 100% by weight of a first polyol component comprising at least one polyoxyalkylene polyol containing oxyethylene residues, said polyol component having an average nominal hydroxyl functionality of from 2 to 4, an average hydroxyl equivalent weight of from 1000 to 5000 and an average oxyethylene content of from 60 to 85% by weight, and
- (b) from 25 to 0% by weight of another polyol component.

14. A method according to any of the claims 11 to 13 wherein the polyol composition has an average nominal hydroxyl functionality of from 2 to 3.

15. A method according to any one of the claims 11 to 14 wherein the reaction mixture further comprises water.

16. A method according to claim 15 wherein the amount of water is less than 2% by weight based on the total weight of the isocyanate-reactive compounds.

17. A method according to any one of the claims 11 to 16 which is carried out at an isocyanate-index of between 90 and 110.

18. A method according to claims 17 which is carried out at an isocyanate-index of between 95 and 105.

19. A reaction system comprising :

- (a) a polyisocyanate component containing at least 85% by weight of 4,4'-diphenylmethane diisocyanate or a variant thereof;
- (b) a polyol composition comprising at least one polyoxyalkylene polyol containing oxyethylene residues, said polyol composition having and average nominal hydroxyl functionality of from 2 to 4, an average nominal hydroxyl equivalent weight of from 500 to 7000 and an average oxyethylene content of between 50 and 85% by weight;
- (c) a chain extender having an average hydroxyl equivalent weight of up to 250;
- (d) water,
- (e) a crosslinking agent, and
- (f) one or more additives conventional to elastomer formulations

Figure 1




Figure 2




Figure 3





Figure 4



5 / 6

Figure 5





Figure 6



INTERNATIONAL SEARCH REPORT

National Application No

PCT/EP 96/05035

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 C08G18/66 C08G18/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	HEPBURN: "POLYURETHANE ELASTOMERS" 1992, ELSEVIER APPLIED SCIENCE, LONDON, GB XP002006846 see page 99, line 19 - page 102, line 5 ---	1
A	JOURNAL OF APPLIED POLYMER SCIENCE, vol. 19, 1975, pages 2493-2513, XP002006845 SEEFRIED ET AL: "THERMOPLASTIC URETHANE ELASTOMERS" ---	1
A	EP 0 611 146 A (TOYO SEIKAN KAISHA) 17 August 1994 see page 4, line 58 - page 5, line 30 see page 18, line 17 - page 19, line 22; claims 1,7; figures 3,4 --- -/--	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* "&" document member of the same patent family

Date of the actual completion of the international search

21 February 1997

Date of mailing of the international search report

12. 03. 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+ 31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 96/05035

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 106, no. 20, May 1987 Columbus, Ohio, US; abstract no. 157765h, OGURO ET AL: "WATER-RESISTANT URETHANE RUBBERS WITH HIGH MECHANICAL STRENGTH" page 67; column 1; XP002006847 see abstract & JP 61 238 816 A (ASAHI CHEMICAL) ----	11
A	US 3 983 094 A (O'SHEA) 28 September 1976 see column 3, line 44 - column 5, line 59; claim 1 ----	11
A	US 4 101 439 A (RUSSELL ET AL) 18 July 1978 see claim 1; example 6 ----	11
A	EP 0 547 765 A (IMPERIAL CHEMICAL INDUSTRIES) 23 June 1993 cited in the application see the whole document ----	11
A	EP 0 013 487 A (IMPERIAL CHEMICAL INDUSTRIES) 23 July 1980 cited in the application see the whole document -----	11

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 96/05035

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-611146	17-08-94	JP-A- 6234184 US-A- 5527616	23-08-94 18-06-96
US-A-3983094	28-09-76	AU-B- 502071 AU-A- 1767876 CA-A- 1081895 DE-A- 2640851 FR-A- 2323716 GB-A- 1548979 JP-A- 52033998 SE-A- 7610054	12-07-79 23-03-78 15-07-80 17-03-77 08-04-77 18-07-79 15-03-77 12-03-77
US-A-4101439	18-07-78	US-A- 4010146 BE-A- 846190 CA-A- 1088697 JP-C- 1453344 JP-A- 52042597 JP-B- 62005932	01-03-77 31-12-76 28-10-80 10-08-88 02-04-77 07-02-87
EP-A-547765	23-06-93	AU-B- 651257 AU-A- 2856992 CA-A- 2084807 CN-A- 1088222 JP-A- 5262845 ZA-A- 9209152	14-07-94 24-06-93 18-06-93 22-06-94 12-10-93 08-03-94
EP-A-13487	23-07-80	AT-T- 6938 AU-B- 532047 AU-A- 5349579 JP-C- 1506908 JP-A- 55089328 JP-B- 63051171 US-A- 4448938	15-04-84 15-09-83 19-06-80 13-07-89 05-07-80 13-10-88 15-05-84